



## TENYMID N2GF6H

**Product Description** PA66 with 30%GF reinforced, used for automotive underhood parts, radiator tank, intercooler tank .

**Material Status** Commercial: Active.

**Availability** Africa & Middle East, Asia Pacific, Europe, Latin America, North America.

**Features** Heat stability and hydrolysis resistance .

**Processing Method** Injection molding.

Physical	Nominal Value	Unit	Test Method
Specific gravity	1.37	g/cm <sup>3</sup>	ISO 1183
Water absorption, at 23°C	3.6	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile modulus	9400	MPa	ISO 527-1/-2
Tensile strength, break	170	MPa	ISO 527-1/-2
Tensile elongation, break	2.6	%	ISO 527-1/-2
Flexural modulus	8800	MPa	ISO 178
Flexural strength	240	MPa	ISO 178
Charpy impact strength, +23°C	52	KJ/m <sup>2</sup>	ISO 179
Charpy impact strength, notched, +23°C	9.5	KJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
HDT, 1.8 MPa under load	252	°C	ISO 75-1/-2
CLTE(Transverse/parallel)	2.2/4.1	10 <sup>-5</sup> /K	ISO 11359-1/-2
Thermal conductivity	0.28	W/(m·k)	DIN 52612
Flammability	Nominal Value	Unit	Test Method
According UL standard	HB	Class	UL 94
Electrical	Nominal Value	Unit	Test Method
Dielectric constant ,100Hz	3.6		IEC 60250
Dissipation factor,100Hz	0.009		IEC 60250
Volume resistivity	1*10 <sup>13</sup>	Ω·m	IEC 60093
Surface resistivity	1*10 <sup>14</sup>	Ω	IEC 60093
Injection	Nominal Value	Unit	Test Method
Melting point,DSC	260	°C	DIN 53765
Melt volum flow rate ,MVR 275/2.15	100	Cm <sup>3</sup> /10min	ISO 1133
Melt temperature range, Injection molding/extrusion	280-305	°C	
Mold temperature range	80-90	°C	



## TENYMID N2GF6H

### **Disclaimer**

#### **Sales products :**

This information and technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved.

Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating TENSURE materials or products will be safe and suitable for use under end-use conditions.

Our products are sold and our advisory service is given in accordance with the current version of our General Conditions of Sale and Delivery.

#### **Test figures :**

Above figures were measured under the condition of 23 °C and RH 50% base on injection molded specimens .They are typical figures, not specifications.

Kindly note that, under certain conditions,

The properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and coloring.

To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace.

The prescribed processing temperatures should not be substantially exceeded.

Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.